



## SERIES 09

A POWDER COATING FOR INTERIOR APPLICATION  
 BASED ON AN EPOXY-POLYESTER BLEND - STANDARD LINE OF PRODUCTS

### Typical applications

- ceiling paneling
- cladding components
- store fixtures and shelving
- office and school furniture
- radiators
- machinery parts
- metal toys

**Standard Packaging** in 20 kg cartons,  
2.5 kg minipack

**Specific Gravity (ISO 8130-2)** 1.2-1.7 g/cm<sup>3</sup>  
depending on pigmentation

**Theoretical Coverage** at 60 µm film thickness:  
9.8-13.8 m<sup>2</sup>/kg depending  
on specific gravity (please  
see also Information Sheet  
no. 1072 - latest edition)

**Storage Stability** 6 months from date of  
delivery under dry conditions  
at no more than 25 °C,  
avoid direct and extended  
heat exposure.

(The shelf life of custom made blanket orders or other  
stock agreements which by their nature are stored over  
longer periods is determined by the original production  
date.)

### Features

- very good mechanical properties
- good flow properties
- good storage stability

### Finish I Colors

- smooth flow - glossy surface,  
approx. 80-95\*
- smooth flow - matte surface,  
approx. 15-30\*
- rough texture - matte surface
- hammertone
- antique (for e-static application only)
- metallic - recycling consistent  
(for e-static application only)
- silver and gold metallic - recycling  
consistent (for e-static application only)

Available from stock in all RAL colors in a  
smooth glossy surface. Any other color can be  
custom made with a minimum order of 60 kg;  
textured and matte finishes require a 200 kg  
minimum order.

\* Gloss level acc. to ISO 2813/60° angle (doesn't apply  
to metallic effect powder coatings). The measured gloss  
level of effect powder coatings can diverge from the  
details given in this product datasheet. The creation of  
tolerance samples is urgently recommended)

## Pretreatment (alternatives)

The following table reflects the common methods of pretreatment with regards to various substrates and applications. In selecting the proper type of pretreatment please observe the suitability of the type of powder coating for a desired application according to the guidelines on page one of this Product Data Sheet.

	ALU-MINUM	GALVANIZED STEEL	STEEL
Degreasing	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
<sup>1)</sup> Chromating	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
<sup>2)</sup> Anodizing	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
<sup>2)</sup> Chrome free	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input type="checkbox"/>
Iron phosphating	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
Zinc phosphating	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Blasting	<input type="checkbox"/>	<input type="checkbox"/>	<input checked="" type="checkbox"/>
<sup>3)</sup> Sweeping	<input type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>

Application	<b>I</b> interior	<b>A</b> architectural
	<b>E</b> exterior	<b>S</b> steel

<sup>1)</sup> acc.to DIN 50939

<sup>2)</sup> acc. to GSB quality and test regulations. The suitability of this type of pretreatment needs to be established through a boiling water test and subsequent cross-hatch adhesion and adhesive tape removal test.

<sup>3)</sup> only for zinc coated parts > 45 µm

<sup>4)</sup> for a two-coat process / TIGER Shield

## Processing


### Corona, Tribostatic\*

\* Suitability of metallic effects for tribo processing must be verified prior to application. Please consult with the relevant Information Sheets, latest edition.


## Cure parameters

(substrate temperature)

### TIGER Drylac® Series 09 smooth flow - glossy surface



### TIGER Drylac® Series 09 rough texture - matte surface I smooth flow - matte surface



## Rough Texture Matte finish and Hammertones

Any deviation from and modification of the recommended application parameters (e. g. film thickness, cure conditions, different application equipment) may lead to variations in the texture. Rough Texture formulations are very sensitive to contamination at the applicator as these contaminations will always "float" to the top of the textured surface. Clean application equipment as well as a clean spraying environment is of the essence.

It is recommended to apply Hammertone effects at an increased film thickness of 100-120 µm. A variation in the cure parameters as well as heavy mass parts may result in different effects. As the effect producing agents in powder coatings float differently from those in wet paint, the effects are reproducible only to a limited extent. For an optimum coating and effect result it is recommended to consistently add virgin powder.

### Please note

Please mind the effect and color differences between a lab match versus an actual production.

Two-coat systems: first coat: apply only half of the curing time acc. to the corresponding Product Data Sheet (provided that no other information is given therein). Second coat: requires then full cure acc. to the relevant Product Data Sheet. Please note, the exact cure conditions (curing time and cure temperature) need to be established individually based on the application and the coating line. Check continuously for intercoat-adhesion!

### Test results

Checked under laboratory conditions on a chromated aluminum test panel which is 0.7 mm thick. Actual product performance may vary due to product specific properties such as gloss, color, effect and finish as well as application related and environmental influences.

test results	test method	Series 09 glossy surface	Series 09 matte surface	Series 09 rough texture matte surface
film thickness	ISO 2360	60-80 µm	60-80 µm	90-120 µm
gloss - 60°	ISO 2813	80-95	15-30	n.a.*
cross cut test 1 mm	ISO 2409	0	0	0
mandrel bending test	ISO 1519	≤ 5 mm	≤ 10 mm	≤ 30 mm
cupping test	ISO 1520	≥ 5 mm	≥ 3 mm	≥ 2 mm
impression hardness	ISO 2815	≥ 90	≥ 90	n.a.*
impact test 20 Inch-pound	ASTM D 2794	no appearance of crack down to the substrate	minor cracks	appearance of cracks down to the substrate
pencil hardness	ASTM D 3260	H	H	n.a.*
drill mill test		ok	ok	ok
determination of resistance to humidity 500 h	ISO 6270-1	max. blistering 1 mm	max. blistering 1 mm	max. blistering 1 mm
salt spray test 500 h	ISO 9227	max. undercutting 1 mm	max. undercutting 1 mm	max. undercutting 1 mm

\*not available



Our verbal and written recommendations for the use of our products are based upon experience and in accordance with present technological standards. These are given in order to support the buyer or user. They are non-committal and do not create any additional commitments to the purchase agreement. They do not release the buyer from verifying the suitability of our products for the intended application. We warrant that our products are free of flaws and defects to the extent as stipulated in our Terms of Delivery and Payment.

As a part of our product information program each of our Product Data Sheets are periodically updated, so that the latest version shall prevail. Therefore, please visit the download area of [www.tiger-coatings.com](http://www.tiger-coatings.com) to make sure you have the most current version of this Product Data Sheet. The information in our Product Data Sheets is subject to change without notification.

**This Product Data Sheet substitutes any and all previous Product Data Sheets and notes for customers published on this subject matter and is only intended to give a general product overview. Please request specific information for products outside of our standard product list (latest version).**

**The Technical Information Sheets and the Terms of Delivery and Payment each in their latest version, available as a download at [www.tiger-coatings.com](http://www.tiger-coatings.com), form an integral part of this Product Data Sheet.**

certified according to  
EN ISO 9001 / 14001



## TIGER Coatings GmbH & Co. KG

Negrellistrasse 36

4600 Wels | Austria

T +43 / (0)7242 / 400-0

F +43 / (0)7242 / 650 08

E [powdercoatings@tiger-coatings.com](mailto:powdercoatings@tiger-coatings.com)

W [www.tiger-coatings.com](http://www.tiger-coatings.com)